

BELTING PRODUCT RANGE- STANDARD LIST

Product Type	Material	Weave	Tensile Strength			Weight (GSM)	Treatment
			Warp Strength Class	Warp Breaking strength (KN/M)	Weft Strength as % of Warp Strength		
NN	Warp- Nylon 6 Weft- Nylon 6	Plain, Broken Twill, Oxford	NN 80 to NN 630	100-785	20% to 60%	260-1800	Black/ Brown/ Special RFL
PP	Warp- Nylon 6,6 Weft- Nylon 6,6	Plain, Broken Twill, Oxford	PP 80 to PP 500	100-625	20% to 60%	260-1450	Black/ Brown/ Special RFL
EP	Warp- Polyester Weft- Nylon 6,6	Plain, Broken Twill, Crowfoot & Special Weaves	EP 80 to EP 800	100-914	20% to 60%	350-2500	Black/ Brown/ Special RFL
EE	Warp- Polyester Weft- Polyester	Plain, Broken Twill, Crowfoot	EE 80 to EE 450	100-580	20% to 50%	350-1350	Black/ Brown/ Special RFL
EN	Warp- Polyester Weft- Nylon 6	Plain, Broken Twill, Crowfoot	EN 80 to EN 450	100-580	20% to 50%	350-1350	Black/ Brown/ Special RFL