

## Product Specifications: High Denier Yarn (Coned)

Product	Denier	B.S (in kgf)	Elongation (in %)	I.E (in %)	Hot Air Shrinkage	Tenacity (in gpd)
840 D (140 Filaments)	850 ± 20	7.2 min	17±2	8.5±1.5	21.5±2.5	8.5
1260 D ( 210 Filaments)	1265 ± 30	11.0 min	17±2	8.5±1.5	21.5±2.5	8.7
1680 D (280 Filaments)	1685 ± 40	14.65 min	17±2	8.5±1.5	21.5±2.5	8.7
1890 D (280 Filaments)	1890 ± 55	16.0 min	17±2	8.5±1.5	21.5±2.5	8.4