

Product Specifications: Low Denier Yarn

Product	Denier	B.S (in kgf)	Elongation (in %)	Tenacity (in gpd)
110 D (24 Filaments)	110 ± 10	0.7 min	22±5	6.36
210 D (24 Filaments)	210 ± 8	1.37 min	23.5±5	6.5
280 D (14 Filaments)	280 ± 15	1.82 min	22.5±5	6.5
420 D (48 Filaments)	425 ± 20	2.85 min	25±5	6.7
550 D (105 Filaments)	550 ± 20	4.0 min	20±5	7.3
630 D (105 Filaments)	630 ± 25	5.3 min	17.5±5	8.4
725 D (140 Filaments)	725 ± 30	5.85 min	21.5±2.5	8